

TECHNICAL BULLETIN – TB111

TILING ADHESIVES FOR USE ADJACENT TO FIRE PLACES

Date. Wednesday, 11 May 2016

INTRODUCTION & SCOPE

The National Construction Code Series (nominally called the Building Code of Australia BCA) requires that fireplaces are installed in accordance with AS/NZS 2918.

Volume Two for class 1 and 10 buildings under heating appliances

Class 1 buildings refers to individual domestic residences, and from Part 3.7.3 on page 280 of NCC 2016 Building Code of Australia, Volume Two,

3.7.3.2 Open fireplace construction

An open fireplace must be constructed as follows (also see [Figure 3.7.3.1](#)):

- (a) All masonry must be constructed in accordance with [Part 3.3](#).
- (b) The front hearth must be constructed of stone, concrete, masonry or similar material so that—
 - (i) it extends not less than 300 mm beyond the front of the fireplace opening and not less than 150 mm beyond each side of that opening; and
 - (ii) its upper surface does not slope away from the back hearth.
- (c) The base of the back hearth must be constructed of stone, concrete, masonry or similar material and any *combustible* flooring or framing members must be situated not less than 150 mm from its upper surface.

Volume One for Class 2-9 buildings under heating appliances.

From Part G2.3 on page 349 of NCC 2016 Building Code of Australia, Volume One,

G2.3 Open fireplaces

An open fireplace, or solid-fuel burning appliance in which the fuel-burning compartment is not enclosed must have—

- (a) a hearth constructed of stone, concrete, masonry or similar *non-combustible* material so that—
 - (i) it extends not less than 300 mm beyond the front of the fireplace opening and not less than 150 mm beyond each side of that opening; and
 - (ii) it extends beyond the limits of the fireplace or appliance not less than 300 mm if the fireplace or appliance is free-standing from any wall of the room; and
 - (iii) its upper surface does not slope away from the grate or appliance; and
 - (iv) *combustible* material situated below the hearth but not below that part *required* to extend beyond the fireplace opening or the limits of the fireplace is not less than 150 mm from the upper surface of the hearth; and

The older versions of the BCA had different requirements, which may apply to previously made installations. Typically the said to have a non-combustible and fire retarded hearth with a minimum width around 400mm from the fire box or grate and 150mm from the sides and back.

This might be a concrete slab, brickwork or Compressed Fibre-Cement sheet which for aesthetic reasons may need to be tiled. For the same reason the fireplace wall surrounds might require tiling onto rendered brick or existing masonry.

A common misconception is that tile adhesives are refractory products and can withstand high temperatures or direct flame contact. Special purpose cements are made for these firebrick type applications and tile adhesives should not be used.

In this bulletin we will look at some of the issues that need to be considered when tiling in this situation.

THERMAL RESISTANCE

The area surrounding a fire becomes quite hot and within a certain distance of the combustion area the temperatures experienced will exceed those that the tile adhesive, or even the tiles themselves can withstand.

The tile adhesives contain polymer materials or in some cases rubber which soften and will degrade when exposed to high temperatures. If the temperature is high enough, the cementitious components can be affected as well. When thermal degradation occurs the adhesive loses its strength and the tiles will de-bond. For this reason tile adhesive shall not be used in the direct fire contact area.

The Australian Standard for tile adhesives has a thermal ageing test regime that exposes the tiles to 70°C and this is the temperature that ARDEX tests its adhesives to withstand in service.

EXPANSION & CONTRACTION

The service temperature of hearth areas adjacent to fires can range from ambient room temperature to maybe 70-80°C and this will create expansion and contraction stresses in the tiles and the adhesive. If these stresses exceed the shear strength of adhesive de-bonding can occur. If the tiles are restrained by the adhesive sufficiently that expansion is restricted cracking or de-bonding may also occur.

The substrate areas will also expand and contract with the changes in temperature and the degree of movement is proportional to temperature range experienced. For example, the creaking-tinkling sounds that occur with metal fire boxes are a result of thermal expansion-contraction of the metal.

INSTALLATION CONSIDERATIONS

When considering installation it is necessary to look at a number of things –

- Type of fire, wood, gas, oil or electric. Wood fires generally create a higher thermal output, and also have the added problem of possible impact from logs or pieces of wood dropped onto the tiles.
- Distance of tiling from the actual fire heating occurs via;
 - ⇒ direct radiation from the fire itself
 - ⇒ thermal conduction through the substrate (i.e. contact of metal hearth parts, and from areas heated by convection or radiation))
 - ⇒ convective heating by air movement (hot air rises so the mantle can be heated this way)
- The types of material used in the construction of the fireplace and surrounds.
- The colour of the tiles (dark heat colours heat up more by radiation) and their heat sensitivity.
- Whether the fire place has a circulation fan which increases the range of convective heating across the floor.

Every installation is different so it is not possible to make 'hard and fast' rules about the service conditions to which the tiling will be exposed. In light of this general recommendations only can be given.

A contact thermometer can be used to check the temperatures reached when the fireplace is in operation.

TILING RECOMMENDATIONS

ARDEX recommends that the tiles to be used for the installation are confirmed as suitable by supplier or manufacturer. Some tiles are subject to greater thermal movement than others, and agglomerated tiles made from an aggregate and resin, and also marble with resin backing may be susceptible to high temperature degradation and should not be used.

The following tile adhesives are suggested for hearth installations for a service temperature up to 70°C. These adhesives have high strengths and flexibility to accommodate movements.

Subfloor type	Recommended adhesive
Concrete	ARDEX ABAFLEX ARDEX OPTIMA ARDEX STS8W + ARDEX E90 ARDEX X77+/- ARDEX E90 ARDEX X18 +/- ARDEX E90
Compressed Fibre-Cement Sheet (CFC) over timber	ARDEX ABAFLEX ARDEX OPTIMA ARDEX STS8W + ARDEX E90 ARDEX X77+/- ARDEX E90 ARDEX X18 +/- ARDEX E90
Concrete or CFC over timber	ARDEX X56



☞ The flexible adhesive X56 contains rubber which at temperatures from around 60-70°C upwards can generate an odour and discolour the grouts. These adhesives have excellent flexibility and will allow for the thermal movements that may occur, but require strict adherence to the maximum recommended temperatures as they have lower heat resistance.

☞ Moisture sensitive stone tiles may be fixed with ARDEX S28N+/- ARDEX E90.

GROUTS

The grouting between tiles must also be flexible and ARDEX recommends the use of ARDEX GROUT BOOSTER with ARDEX FG8, ARDEX WJ50 or ARDEX FSDD grouts.

The use of this additive is described in the product datasheets.

TILING SITUATIONS THAT ARE NOT RECOMMENDED

- ☞ Direct tiling over timber floors adjacent to hearths. This potentially contravenes recommendations in AS2918 and is not recommended for the adhesives indicated.
- ☞ Direct tiling over metal stove parts or metal fixtures near the fireplace.
- ☞ Tiling inside a fireplace (i.e. tiling onto the back or sides of an inbuilt fire place) or areas subject to direct flame contact. Not only can the adhesive failure, the tiles may also fail catastrophically.
- ☞ Tiling in areas that are subject to temperatures that exceed the recommended service temperature are at the installers risk and not warranted by ARDEX. For example BBQs and Pizza ovens are not acceptable applications. There are commercial fire brick and oven suppliers who have materials for this sort of application.
- ☞ Premixed or mastic type adhesives shall not be in this application, they have low glass transition temperatures.
- ☞ Tile over tile installations due possible differential expansions in the tiles.

Problems with heat can be manifested by discolouration of grouts and also any silicone sealant joints. These signs should be seen as a warning that the recommended performance temperature of the adhesive may be being exceeded.

As a general rule, if you can't touch it, it's too hot for the adhesive in the long term.

IMPORTANT

This Technical Bulletin provides guideline information only and is not intended to be interpreted as a general specification for the application/installation of the products described. Since each project potentially differs in exposure/condition specific recommendations may vary from the information contained herein. For recommendations for specific applications/installations contact your nearest ARDEX Australia Office.

DISCLAIMER

The information presented in this Technical Bulletin is to the best of our knowledge true and accurate. No warranty is implied or given as to its completeness or accuracy in describing the performance or suitability of a product for a particular application. Users are asked to check that the literature in their possession is the latest issue.

REASON FOR REVISION

Replacement of S16 with S28N, and STS8 with STS8W. Addition of X18. More detailed references to the NCC

REVIEW REQUIRED

24 months from issue.

Technical Services 1800 224 070. email: technicalservices@ardexaustralia.com

Australia <http://www.ardexaustralia.com>

NSW-HO 61 2 9851 9100, **QLD** 07 3817 6000, **VIC** 03 8339 3100, **SANT** 08 8406 2500, **WA** 08 9256 8600

Customer Service and Sales 1300 788 780

New Zealand Christ Church 64 3373 6900, Auckland 9636 0005, Wellington 4568 5949

Technical Inquiries NZ 0800 2 ARDEX New Zealand <http://www.ardex.co.nz>

Web: Corporate: <http://www.ardex.com>

